

Film LDPE (C4—LLDPE)

Properties	MFR	Density	Stiffness, 23°C	Tensile Strength		Ultimate Elongation		Dart Drop Impact Strength (F50)	Haze	Gloss (45°)	Slip Property*	JHOSPA PL No.	Application
				MD	TD	MD	TD						
Unit	g/10min	g/cm ³	MPa	MPa	MPa	%	%	g	%	-			
Grade													
NUCG-5211B	1.2	0.924	200	32	24	570	700	130	14	50	H	[A]EZar-15577-L	Packaging
NUCG-5212B	1.2	0.924	210	31	26	540	710	120	12	50	MH	[A]EZar-15672-L	Packaging
NUCG-5226	2.0	0.920	180	27	21	610	720	100	13	49	N	[A]EZar-15712-L	Cast

*Slip Property is ranked as (High) VH > H > M > L (Low) * N is additive free

Note •The values are dependent upon using the testing method as indicated and are offered herein as a guide in the use of compound.